



PICKLEPRO

1.0 General Description

ACRYTECH PicklePro is a 100% Acrylic self-crosslinking coating designed to be a playing surface for asphalt or concrete based pickleball courts. PicklePro is factory textured with round, non-angular sand creating a high grip but low abrasion surface. Available colors: Players Choice, Specialty and Custom.

2.0 Safety Guidelines

Avoid contact with eyes, skin and clothing. Refer to SDS for additional information.
Wear proper NIOSH approved respirator when handling silica sand.

3.0 Storage and Handling

Protect from freezing. Store between 4°C (40°F) and 32°C (90°F).
Packaging: 39 gallons in 55 gallon drum (560 lbs.), 30 gallon drum (420 lbs.), 5 gallon pail (70 lbs.). Drums are heavy. Use caution when moving.

4.0 Coverage

Coverage varies upon surface condition and porosity.
Texture coat: .047-.056 gal of concentrate per square yard.

5.0 Preparation Guidelines

5.1 New Construction (asphalt)

- a. Allow asphalt to cure a minimum of 14 days.
- b. Flood surface with water to check for depressions 1/16" or greater. Fill with ACRYTECH Sport Patch (Deep Patch) as needed and allow to cure.

5.2 New Construction (concrete)

- a. For proper bonding concrete should have a broom finish and a vapor barrier installed.
- b. Allow concrete to cure a minimum of 30 days.
- c. Acid bath concrete using muriatic acid. Follow manufacturers' recommendations.
- d. Flood surface with water to check for depressions 1/16" or greater. Fill with ACRYTECH Sport Patch (Deep Patch) as needed.
- e. Prime concrete with ACRYTECH AcryLock.

A product of Stegas, Inc.

www.Tennispaint.com

2660 Easterly Place Decatur, GA 30035



5.3 Existing Construction (asphalt or concrete)

- a. Pressure wash surface to remove dirt, mildew and other contaminants.
- b. Fill cracks with ACRYTECH Sport Patch (Deep Patch) or other crack repair method.

6.0 Application

6.1 All Surfaces-apply with 50 to 60 durometer soft rubber squeegee. Allow 1 to 3 hours for drying time between coats.

- a. Apply one to two coats of Acrylic Resurfacer (rougher surfaces may require two coats).
- d. Apply at least two coats of PicklePro.

7.0 Mixing Instructions

Concentrate	Water (minimum)	Water (maximum)
5 gallons	2 gallons	2.5 gallons
30 gallons	11.5 gallons	14 gallons
39 gallons	15 gallons	18 gallons

8.0 Limitations

DO NOT APPLY WHEN:

- 1. Rain is in the near forecast.
- 2. Surface temperatures exceed 54°C (130°F). Surface temperatures may be reduced by misting surface with water prior to application except on the final coat.
- 3. Do not apply when ambient air temperatures are below 1°C (34°F).

9.0 Physical Properties

Warranty	2 years
Weight per gallon	13.5 lbs
Application and curing Temp.	34-130°F
Average dry time	2 - 4 hours
Cure time before use (min)	48 hrs

A product of Stegas, Inc.

www.Tennispaint.com

2660 Easterly Place Decatur, GA 30035