



## SPORT PATCH TDS

AcryTech Sport Patch is a 100% acrylic latex binder, that when mixed with portland cement and sand, produces a semi flexible latex concrete that is ideal for patching depressions over 1/4" deep and filling cracks larger than 3/8" wide. AcryTech Sport Patch is appropriate for use when applied to asphalt or concrete surfaces, or to previously coated surfaces.

AcryTech Sport Patch is quick drying and has a working time of approximately 30-45 minutes. Please be careful to mix only the amount that can be applied in that time span.

### 1.0 SCOPE

Mix with sand and cement to form a patching compound for filling depressions greater than 1/4" in depth, or to fill cracks larger than 3/8" in width.

### 2.0 MATERIALS

2.1 AcryTech Sport Patch

2.2 Sand

2.3 Portland Cement

### 3.0 MIXING

3.1 Mix sand and cement first, then add ASP and mix again.

3.2	ASP	Type 1 Port. Cem.	Sand
	1 Gal	1/3 Gal	33 lb.

### 4.0 APPLICATION

4.1 Apply with squeegee, straight edge, trowel or spatula.

4.2 Scrape edges of patch with scraper or sand edges of patch with grinding stone.

4.3 Allow 24 hours for curing. Very deep patches 3/4"-1" may require longer curing time.

### 5.0 LIMITATIONS

Deep patch applications in extremely hot weather can experience a false curing. The surface will skim over and the patch will appear to be hard in a matter of hours. Caution should be taken to ensure that the patch has cured throughout, estimated at 24 hours. Do not apply when temperatures are under 50°F or rain is expected within 24 hours.

### 6.0 PHYSICAL PROPERTIES

Color	Milky White
Weight per gallon	8.8 lbs
Application & curing temp.	50-130°F
Cure time (min)	24 hours

A product of Stegas, Inc.

[www.tennispaint.com](http://www.tennispaint.com) | 888-294-0428  
2660 Easterly Place | Decatur, GA 30035