



Key Advantages

- Solvent-free and water-based for easy clean up
- Easily diluted with water
 - Forms a tacky adhesive bond for the first layer of rubber
 - Minimizes clogging of application equipment

Chemistry Type	Carboxylated styrene butadiene [XSB]
Solids (by weight)	50 %
pH	7.5
Tg	-50 °C
Solvent or Water Based	Water
Emulsifier	Anionic
Physical Form	Liquid
Bulk Density	8.3 lb/gal
Brookfield Viscosity	< 250 cps (LVT #2 @ 60 rpm, 25 °C)
Specific Gravity	1.00
Surface Tension	50 dyn/cm
Residue	<150 ppm
Foaming Tendency	Low
Odor	Low
UV Stability	Excellent
Mechanical Stability	Excellent

-
-

Application Information

Application Information

Application Notes	<ul style="list-style-type: none"> • Base Layer Preparation: Pave at least 2" of asphalt over the existing area or on top of a foundation. The asphalt should be allowed to cure and off-gas for 14 days prior to track construction. Do not install during rain because latex may be washed away before drying. Do not install if temperatures drop below 50°F because the latex performance may be compromised. • • •
-------------------	--

Storage & Handling Guidelines

Available Packaging	Totes (IBC) - 2204 lbs approx. 265 gallons
---------------------	--

Handling	<ul style="list-style-type: none"> • See Safety Data Sheet (SDS) for additional product information. • Stir and mix well before using.
----------	--

Recommended Storage Conditions	<ul style="list-style-type: none"> • Keep container tightly covered when not in use. Do not expose product or container to direct sunlight or to freezing temperatures. • Avoid prolonged storage at high temperatures. Store in original packaging. • • •
--------------------------------	---

Recommended Storage Temperature	22 °C (70 °F) This product is not freeze-thaw stable.
---------------------------------	--

Freeze / Thaw Stability	6 Months (when stored as recommended)
-------------------------	---------------------------------------

Shelf Life	
------------	--